


Technical details broadloom

Manufacturing type	Herstellungsart	Mode fabrication	Productie methode			tufted 5/16"
Construction	Struktur	Structure	Structuur			shaggy
Pile composition	Polmateriaal	Couche d'usure	Poolsamenstelling			100% PA
Dye method	Farbgestaltung	Coloration	Kleurverwerking			piece dyed
Primary backing	Trägermaterial	Premier dossier	Tuftdoek			woven
Secondary backing	Rückenausrüstung	Dossier	Rug			action backing
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m ²	900 (+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m ²	1.700 (+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm	20 (+/-)
Total height	Gesamtdicke	Epaisseur totale	Totale dikte	ISO 1765	mm	22 (+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m ²	35.000 (+/-)
Size	Abmessung	Dimension	Afmeting		cm	400
Classification	Klassifikation	Classement	Gebruiksklasse	EN 1307		22+ heavy domestic
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307		LC 4
Castor chair	Stuhlleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985		
Stair suitability	Treppeneignung	Escaliers	Trappengeschikt	EN 1963		
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1		Cfl-S1 glued
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV	≤ 2,0
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω	≥ 10¹⁰
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmte-doorlaatweerstand	ISO 8302	m ² /K/W	
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	α _w	
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔL _w	24 dB
				ISO 10140	ΔL	(1000 Hz)
Colour fastness light	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02		≥ 7-8
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijftechtheid	ISO 105 X12		≥ 4-5

DIBt Nr Z-156.601-1010

Scan the QR code
and go to the productpage
on the website.



Custom colours
> 400m²



EN1307
for use as floorcovering
in buildings (EN 14041)
according to the
manufacturer's specification

CE
16
EN 14041
DOP 000514-002