Technical specifications

Test	Test method	Characteristics
Formaldehyde emission	EN 717-1	E1, < 0,05 ppm
Resistance to staining	EN 438-2	group 1+2: level 5
		group 3: level 4
Light fastness	EN ISO 105-B02	> level 6 blue wool scale
	EN 20 105-A02	> level 4 grey scale
Fire resistance	EN 13501-1	Ignites with difficulty, at least C_{fl}-s1
Height difference between connected elements	ISO 24337	average : ≤ 0,10 mm max: ≤ 0,15 mm
Edge straightness	ISO 24337	≤ 0,3 mm/m
Openings between connected elements	ISO 24337	average: ≤ 0,15 mm max: ≤ 0,20 mm
Static indentation	EN ISO 24343-1	≤ 0,2 mm
Mircroscratch resistance	EN 16094	≤ MSR - A2
Abrasion resistance	EN 15468, App. A	AC4, ≥ 3.000 cycles
	EN 13329, App. E	AC4, ≥ 1.200 cycles
Impact resistance	EN 13329, App. H	≥ 1.200 mm
Thickness swelling	ISO 24336	≤ 18,0 %
Castor chair test	EN 425	25.000 cycles
Classification	EN ISO 10874	

Characteristics

- low maintenance & hard-wearing
- largely resistant to cigarette burns
- durable & impact resistant
- stain resistant
- non-fading and retain their brilliance over many years
- abrasion resistant
- flame resistant
- comfortable underfoot
- well-suited for installation over subfloor heating
- produced from natural sustainable raw materials

Product specifications

Surface	High gloss or Supermatt
Panel size	1295 x 310 x 8 mm
Box	6 panels = 2,409 sqm
Pallet	86,72 sqm = 655 kg
	36 boxes
Utility class	32 | AC 4