

EARTHY PRIVILEGE

WILD LUXURY COLLECTION

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufting 9/64" loop pile Tufté 9/64" loop pile Getuftet 9/64" loop pile Getuft 9/64" loop pile	IMPACT NOISE RATING ISOLATION PHONIQUE TRITTSCHALLVERBESSERUNG GELUIDSISOLATIE	EN ISO 10140-3 26 dB ΔLw
--	--	---	-----------------------------

PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL	100% PA	SOUND ABSORPTION ABSORPTION PHONIQUE SCHALLABSORPTIONSGRAD GELUIDSABSORPTIE	EN ISO 354 0,25 aw
---	---------	--	-----------------------

SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG	Twin back	THERMAL RESISTANCE RÉSISTANCE THERMIQUE WÄRMEDURCHLASSWIDERSTAND WARMTEDOORLAATWEERSTAND	ISO 8302 0,13 m ² K/W
---	-----------	---	-------------------------------------

PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	± 1.150 gr/m ²	FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	ISO 105-B02 ≥ 5-6
---	---------------------------	--	----------------------

TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	± 2.400 gr/m ²	COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥ 4-5
--	---------------------------	---	-------------------------

PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE	± 4,5 mm	FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 C _{FL} -s1 if glued
---	----------	---	--

TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE	± 7,5 mm	WIDTH LARGEUR BREITE BREEDTE	EN ISO 3018 ca. 400 cm
--	----------	---	---------------------------

TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN	± 100.000/m ²
---	--------------------------

PRODIS / GUT	6A636F9D
---------------------	----------

CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 23/31 - LC4
---	------------------------



ITC CO BV
Kanegemstraat 15, B-8700 Tielit
itc-carpets.com

EN 14041 CE
20
ITC CO BV Kanegemstraat 15 - BE 8700 Tielit
DOP: 1011#IE00CV Textile Floor Covering EN1307 Notified Body 2401
my.itc-carpets.com