


# PRIMA

## BOHEMIA COLLECTION

<b>CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR</b>	Tufting 5/16" loop pile Tufté 5/16" loop pile Getuftet 5/16" loop pile Getuft 5/16" loop pile	<b>FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID</b>	EN ISO 105-B02 ≥ 5-6
<b>PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL</b>	100% PP	<b>COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID</b>	EN ISO 105-E01 ≥ 4-5
<b>SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG</b>	Texflor® back	<b>FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG</b>	EN 13501-1 E <sub>FL</sub> -s1
<b>PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT</b>	± 610 gr/m <sup>2</sup>	<b>WIDTH LARGEUR BREITE BREEDTE</b>	EN ISO 3018 ca. 400,500 cm
<b>TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT</b>	± 1.535 gr/m <sup>2</sup>		
<b>PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE</b>	± 6 mm		
<b>TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE</b>	± 8 mm		
<b>TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN</b>	± 43.750/m <sup>2</sup>		
<b>PRODIS / GUT</b>	<b>8DFDFFE1</b>		
<b>CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE</b>	EN 1307 22 - LC1		



ITC co  
Kanegemstraat 15, B-8700 Tielt  
itc-carpets.com

EN 14041
<b>CE</b>
12
<b>BALTA INDUSTRIES</b> Wakkenstwg 2 - BE 8710 Sint-Baafs-Vijve
<b>DOP: 1010#BA0AEL</b>
Textile Floor Covering EN 1307

<a href="http://www.baltamediabank.com">www.baltamediabank.com</a>