


ZENIT

LCT COLLECTION

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufting 1/10" loop pile Tufté 1/10" loop pile Getuftet 1/10" loop pile Getuft 1/10" loop pile	FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	EN ISO 105-B02 ≥ 5-6
PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL	100% PP	COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥ 4-5
SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG	Betumen back Min. 70% recycled content	FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 C _{FL} -1 Centexbel 0493-CPR-0130
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	± 550 gr/m ²	SIZE DIMENSION ABMESSUNG AFMETING	50 X 50 cm
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	± 4.300 gr/m ²	PACKAGING EMBALLAGE VERPACKUNG VERPAKKING	5 m ² /b 20 p/b
PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE	± 4,0 mm		
TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE	± 7,0 mm		
TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN	± 212.760/m ²		
PRODIS / GUT	90CF84A0		
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 22 - LC1		

itc



EN 14041
CE
16
ITC Kanegemstraat 15 - BE 8700 Tielt
DOP: 1010#BIOACL
Textile Floor Covering EN 1307 Notified body 0493
    
www.itc-carpets.com